

PRODUCT SUMMARY

Valspar® Trade Gloss is an advanced, water-based formulation that resists yellowing, offering outstanding flow and levelling, provides a tough and durable finish and superb coverage. This formulation has been specially designed with the trade professional in mind, to achieve the perfect finish for your job, efficiently. You can choose any colour and be confident that it will stay true over time. Faster work, better job. Suitable for interior wood and metal surfaces.

Available in Pure Brilliant White

PRODUCT FEATURES & BENEFITS

- Outstanding flow & levelling
- Washable
- Tough & durable
- Good sag resistance
- Non-yellowing
- High gloss level

RECOMMENDED USES/SUBSTRATES

- Interior wood and metal (all finishes)

APPLICATION

Application method: Brush, roller or sprayer.
For indoor use only. Stir well before use to ensure paint is thoroughly mixed. Do not apply in damp or humid conditions.
Apply when temperature of the surface being painted is above 10°C. When purchasing more than 1 container of the same colour, intermix containers to ensure colour uniformity.

- Do not thin this product.
- Touch dry in 1 hour
- Allow 2–4 hours between coats.

When using a sprayer, make sure you refer to the sprayer user guide for full instructions before use.
Thinning is not recommended.

SURFACE PREPARATION

For best results, read information below before use:

- Bare, absorbent surfaces must be sealed with with Valspar® Trade Primer & Undercoat prior to applying the finishing coat.
- The surface must be clean, dry and free of dust and grease
- Glossy surfaces should be deglossed before painting
- Repair all damaged areas
- Remove old, loose or flaky paint
- When making dramatic colour changes or applying bold colours, we recommend using a Primer & Undercoat prior to applying Valspar® Trade Wood and Metal paint.

Allow at least 1 week for finish to fully harden before washing surfaces with a mild detergent.
Special precautions should be taken during surface preparation of pre-1960's paint surfaces over wood and metal as they may contain harmful lead.

STORAGE & DISPOSAL

After painting, remove as much paint as possible from paint equipment before cleaning with warm, soapy water.

Please dispose of unused paint responsibly. Check with your local authority to see if they provide facilities for the disposal of waste paint. If you have leftover paint that cannot be re-used or stored, do not empty into drains or watercourses. Pour the leftover paint into a box with shredded paper or cat litter, allow it to solidify in a well-ventilated area away from children or pets, and then dispose with household rubbish.

Store paint in a dry area and protect from frost.

HEALTH & SAFETY

Always read the full Health and Safety Information on can prior to use. VOC content: EU limit for this product (Category A/a): 30 g/l (2010). This product contains a maximum VOC content of 5 g/l.
VOC Globe category - LOW
Please contact Valspar Customer Service on 0344 736 9174 or customerservice@valsparpaint.co.uk for the safety datasheet, available on request.

SHIPPING & PACKAGING

Freight Classification: Paint or Paint Related Material
Protect from freezing
Packaging: Case of 1

FURTHER SUPPORT

If you require further support, please contact Valspar Customer Service on 0344 736 9174 or customerservice@valsparpaint.co.uk.
Always read full Health, Safety & Environmental Information on can before use.
(UK) Sherwin-Williams UK Limited, Avenue One, Station Lane, Witney, Oxfordshire, OX28 4XR, UK Tel: 0114 240 9469
(IRL) 644 Jordanstown Road, Aerodrome Business Park, Rathcoole, D24 XE8F Tel: +353 1 2135760

PRODUCT SPECIFICATIONS	
Valspar Trade Wood and Metal Gloss PBW	
Product type:	Acrylic Water based paint
Viscosity:	80.0 - 95.0 KU
Sheen:	60.00 min. 60 deg
VOC (g/l):	19.739999999999998
Solid content of base (before colourant):	Volume Solids: 39.84% Weight Solids: 46.63%
Coverage:	10 m2/L
Recommended film thickness (wet) per coat:	0.8 – 1.0 mm
Recommended film thickness (dry) per coat:	0.08 – 0.12 mm
Touch dry:	1 Hour
Recoat:	2 - 4 Hours
Application Temperature:	10–32°C
Storage temperature:	5–38 deg °C. Do Not Freeze
Testing & Certifications (ISO Ratings):	
Sag resistance: ASTM D4400 (10) Leveling: ASTM D4400 (2) Opacity: ISO 6504 (97.1) Gloss: ISO 2813 Water resistance: ISO 2812-4:2007 (4, recovery 4) Persoz hardness (28d): ISO 1522 Cross-cut test: ISO 2409 (0) Salt-spray test: ISO 9227 (pass) QUV: EN927	
Leave 1 week to cure before washing	